

CALCIUM ALUMINUM ALLOY

ADR 4.3, UN 1393
PACKING GROUP II

1. Specifications

Main % $\pm 2\%$		Impurities % max								
Ca	Al	Mg	Cu	Zn	Fe	N	Ni	Mn	Si	Sn
65	35	0.5	0.05	0.02	0.1	0.05	0.002	0.05	0.01	0.01

2. Applications

Ca/Al alloy could be used as master alloy to remove impurities from Lead alloy and used in Battery and many other industries.

3. Size

30-150mm, 30-100mm in lump shape.

4. Packing

Ca/Al alloy lumps will be packed in small bags under Argon, 5kg net weight per small bag, 25 small bags sealed in 1 UN tested steel drum with 125kg net weight per drum. 4 drums on a wooden pallet and 20 pallets in 1x20' container or 40 pallets in 1x40' container.

In total net weight 10mt in 1x20' container or 20mt in 1x40 container.

